

Atomic-Resolution Z-Contrast Imaging and EELS Study of Ferroelastic and Ferromagnetic Ordering in LaCoO_3

T. Yuan¹, N. Orlovskaya², M. Tanase¹, S. Kell¹, Q. Ramasse³ and R. F. Klie¹

¹ Department of Physics, University of Illinois at Chicago, Chicago, IL, 60607

² Department of Mechanical, Material, and Aerospace Engineering,
University of Central Florida, Orlando, FL, 32816

³ National Center for Electron Microscopy, Lawrence Berkeley National Laboratory,
Berkeley, CA, 94704

The perovskite oxide LaCoO_3 has attracted increasing attention due to its multiple ferroic transitions including ferroelastic and ferromagnetic ordering. At room-temperature LaCoO_3 exhibits creep, which is usually only observed at temperatures close to a material's melting point, while strained LaCoO_3 thin films have been shown to be ferromagnetic at low temperatures. To advance our understanding of these unusual properties, a combination of electron diffraction, atomic-resolution Z-contrast imaging and electron energy-loss spectroscopy (EELS) has been used to study the LaCoO_3 microstructures as a function of applied strain and temperature. A ferroelastic material exhibits a hysteretic stress-strain behavior similar to the hysteresis found in ferromagnetic materials.¹ The coercive stress marks the point where the stress-strain relationship starts to deviate from the expected linear relationship. It has been suggested that the formation of ordered domains or defects occurs at the coercive stress. Therefore, we study LaCoO_3 samples compressed at room temperature above and below the coercive stress, and compare them with untreated samples. In the LaCoO_3 samples compressed above the coercive stress we find superlattice-domains with lattice constant $3a_0$ along the (100), (010) and (001) orientations (see Figure 1). These have been attributed to monoclinic distortions within the rhombohedral lattice.² In untreated LaCoO_3 and samples compressed below the coercive stress we do not find any superstructure, but twin boundaries due to the slight rhombohedral distortion of bulk LaCoO_3 . In contrast to these results, it has been previously shown that epitaxial LaCoO_3 films grown in LaAlO_3 and $(\text{LaAlO}_3)(\text{Sr}_2\text{AlTaO}_6)$ undergo a ferromagnetic ordering transition at temperature close to 80 K.³ We have used a combining of electron diffraction, atomic-resolution Z-contrast imaging, EELS and in-situ cooling experiment to show that the biaxial strain induced by the substrate on the LaCoO_3 film stabilized the intermediate Co^{3+} -ion spin state at low temperature.³ Using energy-loss magnetic circular dichroism (EMCD) method,⁴ we have further obtained angular-resolved EELS of Co L-edges at low- and room-temperature (Figure 2a).³ We can show that there is a ferromagnetic transition in the LaCoO_3 thin film at low temperature, while neither our atomic-resolution Z-contrast image nor the electron diffraction pattern show any sign of a structural transition that can explain the observed magnetic ordering transition (Figures 2b and c).³ Yet, some areas of the strained LaCoO_3 thin films exhibit superlattice domains at room temperature (Figure 3) similar to those of strained LaCoO_3 grains above the coercive stress (Figure 1). In this presentation, we will explore the relationship between the observed ferroelastic and ferromagnetic properties of LaCoO_3 and examine how the observed superlattice domains influence the mechanical and magnetic properties of highly strained LaCoO_3 bulk and thin films.

References:

- ¹ Lugovy et al., Physical Review B 78, 024107 (2008)
- ² J.C. Walmsley et al., J. Mat Sci, 35, 4251-60 (2000)
- ³ R.F. Klie et al., Appl. Phys. Lett, 96(9) (2010)
- ⁴ P. Schattschneider et al., Nature 441 (7092), 486-488 (2006)
- ⁵ Funded by: NSF CAREER Award DMR-0846748




Fig 1: High-resolution phase contrast image of the superlattice domains in LaCoO_3 sample compressed at 110MPa at room temperature




Fig 2: a) Angular-resolved EELS of epitaxial LaCoO_3 films grown in LaAlO_3 according to EMCD method at 94K; the electron diffraction pattern b) at room temperature and c) 94K




Fig 3: Atomic-resolution Z-contrast image of epitaxial LaCoO_3 films grown in LaAlO_3 showing a $3a_0$ superstructure.