

## 4D-STEM Imaging of nanostructural heterogeneities in Ni-20Cr after corrosion in molten salt

Yang Yang<sup>1</sup>, Weiyue Zhou<sup>2</sup>, Sheng Yin<sup>1</sup>, Sarah Wang<sup>3</sup>, Qin Yu<sup>1</sup>, Robert Ritchie<sup>3</sup>, Mark Asta<sup>3</sup>, Ju Li<sup>2</sup>, Michael Short<sup>4</sup> and Andrew Minor<sup>5</sup>


<sup>1</sup>LBNL, United States, <sup>2</sup>MIT, United States, <sup>3</sup>UC Berkeley, United States, <sup>4</sup>Massachusetts Institute of Technology (MIT), Cambridge, Massachusetts, United States, <sup>5</sup>UC Berkeley, Berkeley, California, United States

Nanostructural heterogeneities induced by processes such as chemical segregation, void nucleation, and strain localization are often observed in metals after corrosion, compromising materials performance. It is a prominent challenge to decipher how different kinds of heterogeneities develop and interact with each other to lead to the failure of materials. In molten salt nuclear reactors, the structural materials in contact with the high temperature (above 600°C) salt could also develop such heterogeneities. Previously, it has been shown that many of these structural defects induced by corrosion are localized near the grain boundary (Zhou et al., 2020). While the preferential intergranular corrosion in molten salt may lead to through-thickness penetration (i.e., generation of heterogeneity), it may be slowed down by the introduction of proton irradiation which enhances the diffusion of interstitials to self-heal the regions with excess free volumes (i.e., promotion of homogeneity).

Here, using a combination of advanced electron microscopy techniques including focused-ion-beam lift out, three-dimensional (3D) electron tomography, and four-dimensional scanning transmission electron microscopy (4D-STEM), we report on the characterization of the localized structural heterogeneities in a Ni-20Cr alloy induced by molten-salt corrosion (Fig. 1). Molecular dynamics simulation (MD) and density functional theory (DFT) simulations have also been performed to elucidate the generation of excess free volumes during the dealloying process. In this presentation, we attempt to explain how defect transport near the grain boundaries induces void growth and how the void morphology is affected by the nonequilibrium point-defect concentrations and the local strain "hot spots".

### Acknowledgments

Primary support for this work came from FUTURE (Fundamental Understanding of Transport Under Reactor Extremes), an Energy Frontier Research Center funded by the U.S. Department of Energy, Office of Science, Basic Energy Sciences. Y.Y., S.Y., Q.Y. and R.O.R. were supported by the Director, Office of Science, Office of Basic Energy Sciences, Materials Sciences and Engineering Division, of the U.S. Department of Energy under Contract No. DE-AC02-05-CH11231 within the Mechanical Behavior of Materials (KC 13) program at the Lawrence Berkeley National Laboratory. The authors acknowledge support by the Molecular Foundry at Lawrence Berkeley National Laboratory, which is supported by the U.S. Department of Energy under Contract No. DE-AC02-05-CH11231. J.L. acknowledges support by DOE Office of Nuclear Energy, Nuclear Energy University Program (NEUP) under Award Number DE-NE0008751. W.Z., M.J., and M.P.S. gratefully acknowledge funding from the US Department of Energy Nuclear Energy University Program (NEUP) under Grant No. 327075-875J. S.Y.W. was supported by the National Science Foundation Graduate Research Fellowship (No. DGE 1752814).



**Figure 1.** (a) An overview of the research; (b) Elemental mapping showing the local Ni enrichment and Cr depletion at a corroded GB; (c) 4D-STEM characterization using a bullseye condenser aperture (Zeltmann et al., 2020); (d) MD/DFT modeling of the corrosion process.

#### References

- [1] Zeltmann, S. E., Müller, A., Bustillo, K. C., Savitzky, B., Hughes, L., Minor, A. M. & Ophus, C. (2020). Patterned probes for high precision 4D-STEM bragg measurements. *Ultramicroscopy* **209**, 112890. <https://linkinghub.elsevier.com/retrieve/pii/S0304399119302451>.
- [2] Zhou, W., Yang, Y., Zheng, G., Woller, K. B., Stahle, P. W., Minor, A. M. & Short, M. P. (2020). Proton irradiation-decelerated intergranular corrosion of Ni-Cr alloys in molten salt. *Nature Communications* **11**.