

Halide perovskite materials and devices

Sang Il Seok and Tzung-Fang Guo, Guest Editors

Halide perovskites have attracted tremendous attention from many researchers recently, particularly for their excellent optoelectronic properties in applications such as photovoltaic solar cells and light-emitting diodes. In recent years, the application of halide perovskites has rapidly extended into nanoelectronics, such as thermoelectric, memory, and artificial synapse applications. Halide perovskites can be synthesized easily, even at relatively low temperatures, and organic and inorganic ions can even coexist in one crystal structure. Moreover, the structural flexibility is excellent, where two- and three-dimensional crystals can be linked together. The combination of various types of halide ions not only controls the physical properties of the halide perovskite, but also facilitates control of the bandgap by varying the size of nanoparticles when they exhibit quantum effects. Halide perovskites thus provide an excellent platform for optoelectronics with interesting optical, electrical, and magnetic properties. The articles in this issue introduce the wide range of basic properties and potential applications of halide perovskites.

Introduction

The name “perovskite” honors Russian mineralogist L.A. Perovski, who first characterized the structure of the mineral calcium titanium oxide (CaTiO_3). A perovskite material has the chemical formula of ABX_3 , where A is a cation with a large ionic radius, B is a metal cation, and X is an anion; its crystallographic structure is the same as that of CaTiO_3 . The easiest way to describe the perovskite structure is to display it as an AX_{12} cuboctahedron that shares its edges with a BX_6 octahedron, as shown in **Figure 1**.¹ This oxide perovskite structure is energetically stable and is flexible enough to structurally accommodate a variety of elements, which facilitates adjustment and choice of materials to achieve the desired properties. Through successful application as dielectric and piezoelectric materials, the excellent structural properties that are achieved can be used in almost any application, such as superconductors, multiferroics, batteries, fuel cells, photovoltaic electrodes, catalysts, resistive switches, and sensing materials.^{2–4}

Halide perovskites have the same perovskite structure as oxide perovskites, but monovalent halide ions occupy the sites populated by divalent oxygen ions in an oxide perovskite. Therefore, halide perovskites can only host inorganic metal cations, such as Pb^{2+} , Sn^{2+} , and Ge^{2+} , with a valence state of 2^+ to satisfy charge neutrality. This means that diversity in terms of composition can be greatly limited compared to that of oxide perovskites which can also accept trivalent and tetravalent cations at the B site. This limitation, however, is compensated by the possibility of lower-temperature synthesis of

halide perovskites compared to oxide perovskites. This allows organic cations to be accommodated in the halide perovskite and has led to the development of a new class of materials called inorganic–organic hybrid halide perovskites.

Inorganic–organic hybrid perovskites are well known for their success in solar power generation. In 1978, Weber⁵ had already studied the basic crystallographic properties. The acceptance of organic cations in the A position of the perovskite structure could yield new properties that conventional oxide perovskites do not have, which presents a new avenue in materials science. Moreover, organic cations allow easy conversion of a three-dimensional (3D) perovskite to a two-dimensional (2D) structure depending on the size of the ions, and new categories of material groups are expected to be created because a combination of 3D and 2D structures is possible. For example, higher dielectric and piezoelectric properties than those of oxide perovskites BaTiO_3 or $\text{Pb}(\text{Zr,Ti})\text{O}_3$ were observed in the 2D perovskite ferroelectric (4-amino tetrahydropyran)₂ PbBr_4 .⁶ As shown in Figure 1, applications using halide perovskites continue to expand to optoelectronic devices, such as solar cells and light-emitting diodes (LEDs); nanoelectronic devices such as thermoelectric and memory devices; and artificial synapses.^{7–9}

Inorganic–organic hybrid perovskite materials such as methylammonium lead triiodide, formamidinium lead triiodide, and formamidinium tin triiodide are especially attracting increasing attention owing to their unique and interesting optical and electrical properties, such as high molar extinction

Sang Il Seok, School of Energy and Chemical Engineering, Ulsan National Institute of Science and Technology, South Korea; seoksi@unist.ac.kr
Tzung-Fang Guo, Department of Photonics, Advanced Optoelectronic Technology Center, National Cheng Kung University, Taiwan; guotf@mail.ncku.edu.tw
doi:10.1557/mrs.2020.140

perovskites. They ask, “Can we find and identify ways to prove the presence or absence of defect tolerance?”

Xiao et al.¹⁴ in their article in this issue discuss the post-treatment methods of achieving higher performance in perovskite photovoltaics. It is noteworthy that the development of new fabrication techniques and composition engineering has greatly contributed to improving the device efficiency and performance. This article overviews post-treatment methods and their impact, and summarizes the fundamentals of nonradiative energy loss in perovskite solar cells at the current level of understanding. It also reviews recent advances in mitigating the energy loss by post-treatment techniques and provides key ideas for further development.

Apart from the realization of improved efficiencies, these perovskite materials still face stability issues hindering their progress toward commercialization. In their article in this issue, Zhang et al.¹⁵ provide a comprehensive overview and seek solutions through hole-conductor-free perovskite solar cells. Although organic hole-transport materials, such as Spiro-OMeTAD, employed in the fabrication of solar cells yield higher efficiency, they impose a drawback of poor stability. This can be potentially addressed by excluding the hole-transport layers, which transport or extract the hole carriers generated in perovskite active layer under solar irradiation, to take advantage of the superior hole- and electron-transport properties of the perovskite itself. This strategy is presented in detail to enlighten readers, and their prospective application is discussed to pique interest among researchers. The device structure, electron-transport materials, morphology and composition of halide perovskites, electrode materials, and energy-level alignment affect the efficiency of hole-conductor-free perovskite solar cells. The strategies currently applied to optimize the efficiency of various hole-conductor-free perovskite solar cells are presented and their impact on stability and efficiency are discussed. Various device structures of hole-conductor-free perovskite solar cells are presented, and their significant stability and improved efficiency are summarized. Finally, a hint of the future scope and development trend of hole-conductor-free perovskite solar cells is provided to address their low-efficiency issue.

The advantage of tunable and narrow emissions covering the whole visible region in nanocrystalline metal-halide perovskites has invoked much interest among researchers. Perovskite nanocrystals have emerged as a new generation of light-emitting materials and have found interesting applications in optically pumped white-emissive LEDs and monochromatic electrically driven LEDs. Although the use of perovskite nanocrystals as active materials for various optoelectronic devices has been explored extensively, they face limitations for light-emitting applications arising from their low photoluminescence quantum efficiencies (PLQEs). This is because of the presence of mobile ionic defects and the small exciton-binding energy. A promising approach to improve the PLQEs is to develop techniques to prepare

nanocrystals with increased exciton binding energy and reduced defects. A wide range of reports have been available since 2004 concerning this objective. Because a variety of synthetic approaches have been established to precisely control the compositions and microstructures of perovskite nanocrystals, it is important to consider such milestones in the field of materials development and device integration based on perovskite nanocrystals. In their article in this issue, Xu et al.¹⁶ summarize these recent advances in light-emitting nanocrystalline perovskites, from synthesis control to device integration. Despite tremendous development, many issues and challenges, including stability, lead poisoning, and accessible processing, remain. These are discussed to enlighten readers about the existing challenges and generate innovative ideas among young researchers to overcome them in the near future.

Outlook

Over the past decade, the performance of optoelectronic devices, such as solar cells and LEDs, based on halide perovskites, has evolved significantly in terms of efficiency and stability. In particular, halide perovskites can now be fabricated as high-efficiency devices using a low-temperature solution process. If long-term stability can be improved, the halide perovskite will become an appealing material that satisfies even low-cost requirements. Moreover, because halide perovskites can accept and incorporate organic cations within one crystal structure, new physical properties may appear depending on the type of organic cations used. Therefore, these materials are expected to be highly scalable for a variety of applications. This will require extensive research, from the basic properties to practical devices. We have briefly reviewed and highlighted various aspects of halide perovskite materials here. We hope the articles in this issue will inspire researchers to utilize these materials in a broad range of research fields, and encourage new and especially early career researchers to enter the field and contribute.

References

1. W. Xu, H. Cho, Y.-H. Kim, Y.-T. Kim, C. Wolf, C.-G. Park, T.-W. Lee, *Adv. Mater.* **28**, 5916 (2016).
2. M. Kubicek, A.H. Bork, J.L.M. Rupp, *J. Mater. Chem. A* **5**, 11983 (2017).
3. R. Pandey, G. Vats, J. Yun, C.R. Bowen, A.W.Y. Ho-Baillie, J. Seidel, K.T. Butler, S.I. Seok, *Adv. Mater.* **31**, 1807376 (2019).
4. W.-J. Yin, B. Weng, J. Ge, Q. Sun, Z. Li, Y. Yan, *Energy Environ. Sci.* **12**, 442 (2019).
5. D. Weber, *Z. Naturforsch.* **33 b**, 1443 (1978).
6. X.-G. Chen, X.-J. Song, Z.-X. Zhang, P.-F. Li, J.-Z. Ge, Y.-Y. Tang, J.-X. Gao, W.-Y. Zhang, D.-W. Fu, Y.-M. You, R.-G. Xiong, *J. Am. Chem. Soc.* **142**, 1077 (2020).
7. T. Liu, X. Zhao, J. Li, Z. Liu, F. Liscio, S. Milita, B.C. Schroeder, O. Fenwick, *Nat. Commun.* **10**, 5750 (2019).
8. H. Yu, J. Gong, H. Wei, W. Huang, W. Xu, *Mater. Chem. Front.* **3**, 941 (2019).
9. K. Hong, Q.V. Le, S.Y. Kim, H.W. Jang, *J. Mater. Chem. C* **6**, 2189 (2018).
10. National Renewable Energy Laboratory, Best Research-Cell Efficiency Chart (2019).
11. D.H. Fabiani, R. Seshadri, M.G. Kanatzidis, *MRS Bull.* **45** (6), 467 (2020).
12. S. Lee, K. Choi, C. Min, M.Y. Woo, J.H. Noh, *MRS Bull.* **45** (6), 439 (2020).
13. S. Kumar, G. Hodes, D. Cahen, *MRS Bull.* **45** (6), 478 (2020).
14. S. Xiao, Y. Li, S. Zheng, S. Yang, *MRS Bull.* **45** (6), 431 (2020).
15. D. Zhang, Y. Rong, Y. Hu, A. Mei, H. Han, *MRS Bull.* **45** (6), 449 (2020).
16. L. Xu, M. Worku, Q. He, B. Ma, *MRS Bull.* **45** (6), 458 (2020). □




Sang Il Seok is a distinguished professor in the School of Energy and Chemical Engineering at the Ulsan National Institute of Science and Technology (UNIST), South Korea. He obtained his PhD degree from Seoul National University, South Korea. His current research focuses on the preparation of functional inorganic–organic hybrid materials and their application to energy devices, including perovskite solar cells. In 2017, he received the Korea Scientists Award from the Korean Government, and in 2019, he received the Kyung-Ahm Prize from the Kyung-Ahm Education and Cultural Foundation. Seok can be reached by email at seoksi@unist.ac.kr.



Tzung-Fang Guo has been a faculty member in the Department of Photonics at National Cheng Kung University, Taiwan, since 2003. He received his PhD degree in materials science and engineering from the University of California, Los Angeles, in 2002. His current research focuses on the magnetic field effect of organic electronic devices and perovskite-based photovoltaics and light-emitting diodes. He received an Academic Outstanding Research Award from the Ministry of Science and Technology, Taiwan in 2018, and became a Fellow of SPIE, the International Society for Optics and Photonics in 2020. Guo can be reached by email at guotf@mail.ncku.edu.tw.

SPECIAL ONE-TIME EVENT



2020 **MRS**[®] SPRING AND FALL MEETING & EXHIBIT

Presented Jointly

November 28 – December 4, 2020 | Boston, Massachusetts

We are excited to announce this Joint **2020 MRS Spring & Fall Meeting** and hope you'll plan to join us! We have a strong community and we thank all those volunteers who have stepped forward to make this a reality. Visit mrs.org/spring-fall-2020 for continued updates and a list of Frequently Asked Questions.

Call for Exhibitors

A unique opportunity to present your innovative products and services to an international audience of materials science and engineering professionals.

Sign up today!

- ▶ **General Interest**
NEW! Materials Opportunities in Medicine and Public Health
- ▶ **Broader Impact**
- ▶ **Electronics and Optics**
- ▶ **Energy**
- ▶ **Flexible, Wearable Electronics, Textiles and Sensors**
- ▶ **Materials Theory, Characterization and Data Science**
- ▶ **Nanomaterials and Quantum Materials**
- ▶ **Soft Materials and Biomaterials**
- ▶ **Structural and Functional Materials**

mrs.org/spring-fall-2020