

nism. "These are 'Russian matryoshka doll-like' structures," Ruoff said. "One nanotube is nested inside of another, which is inside of another, and so on. For the MWCNTs we mechanically loaded, there would be typically 10 to 40 nested cylinders."

"Our method of 'nano-welding' these onto the cantilever tips, which are our 'fingers' for holding and pulling, is to focus the electron beam onto the MWCNT, where it is loosely attached by the relatively weak van der Waals forces to the cantilever tips," said Ruoff. "Doing this causes residual hydrocarbon gases in the electron microscope to be decomposed and to build up a small carbonaceous deposit. This deposit is the strong attachment that holds the nanotubes in place during the experiment."

The method needs further development, he said. About one-half of the MWCNTs attached in this manner still broke at the attachment site rather than within the loaded nanotube section after the load was applied. But the other half represented 19 separate MWCNT tensile-loading experiments.

Ruoff said, "Since the attachment is to the outermost shell, and the interaction between these nested nanotubes in a multi-walled nanotube is relatively weak, one might expect that the outermost shell will carry the load and break, with pullout of the inner shells then occurring immediately after the break. This is exactly what we observed."

"When we take account of the lower density of carbon nanotubes as compared to high-grade steels, the outer shell is about 50 to 60 times stronger. This suggests that there are future applications for very lightweight, high-strength cables and composites, where the carbon nanotubes are the load-carrying element," Ruoff said.

### V<sub>2</sub>O<sub>5</sub> Nanofibers Used in Fabricating Field-Effect Transistor

G.T. Kim, J.G. Park, and Y.W. Park of Seoul National University, and J. Muster, V. Krstic, S. Roth, and M. Burghard of the Max-Planck Institute in Stuttgart have demonstrated that vanadium pentoxide (V<sub>2</sub>O<sub>5</sub>) nanofibers can be readily deposited in controllable densities on chemically modified Si/SiO<sub>2</sub> substrates. The feasibility of using these nanofibers for electrical conduction in nanoscale devices is being investigated. Current attempts to use carbon nanotubes for this purpose suffer from the tendency of the nanotubes to form in dense networks, requiring potentially damaging ultrasonic treatment to separate the individual fibers. The deposi-

tion of V<sub>2</sub>O<sub>5</sub> nanofibers requires no such separation step.

As reported in the April 3 issue of *Applied Physics Letters*, nanofibers of V<sub>2</sub>O<sub>5</sub> of molecular thickness are synthesized from ammonium(meta)vanadate and an acidic ion exchanger. To fabricate a field-effect transistor (FET), the nanofibers are deposited on a Si/SiO<sub>2</sub> substrate, and 15-nm-thick Au/Pd electrodes are patterned on the surface 100 nm apart using electron-beam lithography. A 300-nm-thick layer of thermally grown SiO<sub>2</sub> insulates the electrodes from a back gate consisting of the substrate doped with As<sup>+</sup> ions. The measured resistance of the V<sub>2</sub>O<sub>5</sub> fibers connecting the electrodes ranged between 200 MΩ and 300 MΩ. This relatively high resistance limits the performance of the FET in its present version; further investigation using fibers with higher conductivity (such as VO<sub>2</sub> or V<sub>2</sub>O<sub>3</sub>) is planned.

### Ultrafast Laser Pulses Facilitate Storage and Retrieval of Quantum Phase Information in Cesium Rydberg States

Using ultrafast lasers and a beam of cesium atoms, physicists at the University of Michigan have created a database that

stores and retrieves data in atomic quantum phases. As reported in the January 21 issue of *Science*, a computer randomly assigned data values to one quantum state of a single cesium atom. Using an ultrashort pulse of intense laser light, the scientists stored the information in the assigned quantum state by flipping the quantum phase or inverting the quantum wave for that state. Less than 1 ns later, the same atom was hit by a second laser pulse, which located the stored data by amplifying the flipped quantum state and suppressing all other states in the wave packet. The laser pulse used to store the data was produced by filtering a 100-fs laser pulse centered approximately on  $\lambda = 785$  nm. The cesium atomic states interrogated were Rydberg *p*-states, with principal quantum numbers ranging from  $n = 29$  to  $n = 38$ .

Philip H. Bucksbaum, the Otto Laporte Professor of Physics at Michigan, said that L.K. Grover, in a 1997 paper published in *Physics Review Letters*, speculated that quantum 2-state data registers would be a faster, more efficient way to search and retrieve data than the classical binary system currently used because the rules of quantum mechanics allow a search in many locations simultaneously. "We test-

# K-TEK

International Inc.

- ▼ Beryllium High Purity Foil
- ▼ Beryllium Vacuum Assemblies
- ▼ High Purity Target Material
- ▼ SPM Cantilevers/Tips
- ▼ SPM Calibration Gratings
- ▼ Positioning Instrumentation
- ▼ Monochromator Crystals



7086 SW Beveland Street  
 Portland, OR 97223 USA  
 Tel: 503.624.0315 • Fax: 503.624.0735  
 www.ktekintl.com  
 E-mail: science@ktekintl.com

Circle No. 16 on Inside Back Cover