

Atomic Mapping of Domain Configurations in Ferroelectric Thin Films

Y. L. Tang¹, Y. L. Zhu¹, Y. Liu¹, Y. J. Wang¹, and X. L. Ma^{1,2}

¹ Shenyang National Laboratory for Materials Science, Institute of Metal Research, Chinese Academy of Sciences, Wenhua Road 72, 110016 Shenyang, China

² School of Materials Science and Engineering, Lanzhou University of Technology, Langongping Road 287, 730050 Lanzhou, China

Atomic-scale information is of critical importance for understanding intrinsic characteristics of advanced functional materials such as ferroelectrics, magnets, superconductors and catalysts. For example, it is often the small deviations from symmetry in atom positions and the resultant strains that allow ferroelectric oxides, used in computer memory chips, to store charge/information or to resonate with magnets as composite multiferroics. Ferroelectric crystals feature asymmetric or polar structures that are switchable under an external field, holding promise for random access memories, thin-film capacitors and actuators [1].

PbTiO₃ is a ferroelectric with a tetragonal structure. We have grown a number of PbTiO₃/SrTiO₃ multilayered samples on orthorhombic GdScO₃(110) substrates by pulsed laser deposition (PLD), using a Lambda Physik LPX 305i KrF ($\lambda=248$ nm) excimer laser. We observe the as-grown epitaxial PbTiO₃/SrTiO₃ multilayer films in which the electric dipoles at domain-walls of ferroelectric PbTiO₃ are characterized by means of aberration-corrected scanning transmission electron microscopy (AC-STEM) [2-6]. We also rationalize the experimental observation via phase-field modeling [3].

Besides the well-accepted head-to-tail 90° uncharged domain-walls (UCDWs), we have identified not only head-to-head positively charged but also tail-to-tail negatively charged domain-walls (CDWs). The widths, polarization distributions, and strains across these charged domain-walls are mapped quantitatively at atomic scale, where remarkable difference between these domain-walls is presented [4].

We observe not only the atomic morphology of the flux-closure quadrant but also a periodic array of flux-closures in ferroelectric PbTiO₃ films, mediated by tensile strain on a GdScO₃ substrate. We directly visualize an alternating array of clockwise and counter-clockwise flux-closures, whose periodicity depends on the PbTiO₃ film thickness. In the vicinity of the core, the strain is sufficient to rupture the lattice, with strain gradients up to 10⁹/m [5]. We also observe a 3D polarization texture of a four-fold flux closure domain. Ferroelectric displacement analysis based on aberration-corrected scanning transmission electron microscopic imaging reveals highly inhomogeneous strains with strain gradient above 10⁷/m. These giant disclination strains significantly broaden the 90° domain walls, while the flexoelectric coupling at 180° domain wall is less affected [3].

We find that the coupling of 90° and 180° domain walls with dislocations may induce the formation of 90° charged domain walls and some other novel metastable domain configurations. Such domain patterns are observed to relax with 180° domain walls annihilation and the reversal of polarization directions of *a*- and *c*-domain. The configurations of both dislocations and stacking faults may lead to a dramatic change of the domain patterns. Unusual dislocation strain field is identified for a dislocation with the burgers vector 45° apart from a 90° domain wall [6]. In addition, we perform large-scale strain

analysis by employing the combinations of geometrical phase analysis (GPA) and AC-STEM imaging, which makes the investigation of ferroelectric domain structures accurate and straightforward [7,8].

References:

- [1] JF Scott, *Science* **315** (2007), P954.
 [2] WY Wang *et al.*, *Adv. Mater. Interfaces* (2015), DOI: 10.1002/admi.201500024.
 [3] YL Tang *et al.*, *J. Mater. Res.* (2016), DOI: 10.1557/jmr.2016.259.
 [4] YL Tang *et al.*, *Sci. Rep.* **4** (2014), 04115.
 [5] YL Tang *et al.*, *Science* **348** (2015), P547.
 [6] Y Liu *et al.*, *Adv. Mater. Interfaces* (2016), DOI: 10.1002/admi.201600342.
 [7] YL Tang, YL Zhu, XL Ma, *Ultramicroscopy* **160** (2016), P57.
 [8] The authors acknowledge funding from the National Natural Science Foundation of China (No. 51231007, 51571197, 51501194, 51671194 and 51521091), National Basic Research Program of China (2014CB921002), and the Key Research Program of Frontier Sciences CAS (QYZDJ-SSW-JSC010). YL Tang acknowledges the IMR SYNL-T.S. Kê Research Fellowship and the Youth Innovation Promotion Association CAS (No. 2016177).




Figure 1. Two-Dimensional mappings of structural and electric behaviors showing the differences between 90° CDWs and 90° UCDWs. (a, b) Out-of-plane lattice spacing mapping for the 90° PCDW and NCDW. (c, d) Lattice gradient mappings (lattice gradient of the out-of-plane lattice mappings along in-plane direction, mapped unit-cell by unit-cell) for the two types of domains. Note the alleviated lattice gradient across the 90° CDWs, especially of the 90° PCDW, compared with sharp lattice gradient across the 90° UCDWs. (e, f) P_s angle mappings for the two types of domains. The definition of 0° , 90° , 180° , and 270° are marked with colored arrows with corresponding color-scale. In case of the 90° PCDW, the P_s angles are markedly disordered.